



PRODUCT DATA SHEET

AZCOTHANE REO

POLYURETHANE FORTIFIED MICRO-FIBRE REINFORCED WATER BASED WATERPROOFING MEMBRANE

Description

Azcothane Reo is a water-based, flexible, high performance, polyurethane fortified acrylic emulsion waterproofing membrane incorporating micro-fibres and formulated for use in demanding exposed, under tile, underground and immersed waterproofing applications.

The incorporation of reinforcing micro-fibres creates an internal reinforcing lattice thereby eliminating the need for external reinforcing.

Azcothane's Reo formulation complies with AS4858:2004 and is generally applied in accordance with AS3740:2004.

It is liquid applied and cures to form a durable, flexible, strong, uv resistant, odourless, seamless, and impervious waterproofing membrane. It does not re-emulsify after it has fully cured making it ideal for long-term waterproofing. It will not stain grout or tiles.

Uses

Azcothane Reo has been specifically designed for exposed, under-tile, underground and immersed waterproofing requirements included the long-term waterproofing of:

- Exposed concrete and metal roofs
- Wet areas within buildings (shower recesses, bathrooms & laundries)
- Ponds & water features
- Concrete and timber decks
- Terraces and balconies (under tiles)
- Concrete slabs
- Retaining walls
- Planter boxes
- Water retaining structures
- Tiles or topped areas

Suitable Surfaces

Azcothane Reo is suitable for properly primed: Concrete, cement, cement render, block work, brick, masonry, FC sheeting and CFC sheeting, plaster board and timber, plywood and particle board (if primed with Duram Primeseal) and metal (if primed with a metal primer).

Note: We do not regard particle board as a suitable substrate for wet areas and if possible should be replaced or covered with CFC sheeting - particularly in shower recesses. If covered we recommend that the particle board be coated with 2 coats of Duram Primeseal and joins and corners sealed with a polyurethane sealant prior to laying the CFC sheeting.

Azcothane Reo may be applied to slightly damp surfaces but the product will not fully cure if the surface remains damp. This process takes longer than if the surface was allowed to dry before application. The surface must dry before the membrane can dry. Freedom from surface water, continual dampness is essential. Priming of all surfaces is highly recommended.

Additional Uses

Azcothane Reo has been formulated as a completely versatile waterproofing membrane, available in a range of colours, making it suitable for:

- Exposed to direct sunlight on roofs (flat, sloping or metal deck).
- Under tile applications - wet areas, balconies, terraces etc.
- Underground applications - retaining walls, planter boxes and garden areas.
- Immersed applications - ponds and water features.

Specification

The information contained in this product data sheet is typical but does not constitute a full specification as conditions and specific requirements may vary from project to project. The instructions should be considered as a minimum requirement but the applicator or contractor must use their skill, knowledge and experience to carry out additional works as may be necessary to meet the requirements of the project. Specification for specific projects should be sought from the Company in writing.

Limitations

Azcothane Reo is not designed as a trafficable membrane although infrequent maintenance foot-traffic would be acceptable.

Benefits and Advantages

Azcothane Reo is a versatile membrane suitable for many demanding waterproofing applications:

- Polyurethane fortified
- Internally reinforced with micro-fibres.
- It meets the criteria of AS4858:2004 and is applied in accordance with AS3740:2004.
- UV resistant - suitable for direct exposed to sunlight.
- Not a hazardous product and not flammable. Water based.
- Flexible (tested to class 111 - highest tensibility) & strong.
- Formulated for wet area and under tile applications.
- Does not re-emulsify after proper curing.
- Tough and durable.
- Dries fast.
- Compatible with most tile adhesives.
- Easy to apply.
- Virtually odourless.
- Will not stain grout or tiles.
- Available in range of colours.

Precautions in Use

The product is considered safe to use if used correctly, as intended and proper industrial hygiene and practices are used. Always observe safety precautions.

Priming and Surface Preparation

Good preparation is essential. Surfaces must be sound, stable, dry, clean and free of dust, rust, loose, flaking, friable material and substances that may diminish adhesion.

Priming - Surfaces should ideally be primed with Duram Primeseal applied at no less than 1 litre per 4m² and allowed to dry. Duram Primeseal must be used for roofs and exposed areas, timber and particle board surfaces, bitumen or where there is a risk of entrapped moisture in the substrate which may cause the membrane to bubble.

Metal surfaces must be treated for rust and apply a metal etch primer.

Priming is adequate if the surface has a solid off-white appearance. Particle board and bitumen surfaces should be primed with 2 coats of Duram Primeseal.

Alternative primers such as Duram WB Primer, may be used in non-exposed areas and where the moisture content of the surface is very low applied and applied at no less than 1 litre per 4m². Allow WB Primer to fully dry before top coating.

Excessively porous, friable and dusty surfaces may require an additional priming coat.

Please refer to the product data sheets of the stated primers.

DURAM INDUSTRIES (PTY) LTD ACN 002 968 809 ABN 77 002 968 809
The Ultimate in Waterproofing & Protective Coating Technology

NEW SOUTH WALES: 51 Prince William Drive, Seven Hills, NSW 2147
QUEENSLAND: Unit 4, 29 Collinsvale Street, Rocklea QLD 4106
NEW ZEALAND: Consolidated Alloys (NZ) Ltd
55 Maurice Rd, Penrose, Auckland, New Zealand

Tel: (02) 9624 4077 Fax: (02) 9624 4079
Tel: (07) 3255 6478 Fax: (07) 3255 6258
Tel: 001164 9 622 9110 Fax: 001164 9 622 9119
Web: www.dlmwallace.co.nz

Detailing Preparation

Corners: Prime as required.

Apply an adequate flexible polyurethane sealant, in accordance the manufacture's instruction and tool off to form a solid, coved or 45° fillet extending at least 10mm on to the adjacent surfaces. Allow sealant to cure. Apply the Duram membrane directly over the cured sealant and on the adjacent surfaces.

For Additional waterproofing protection the following additional steps should be taken

Lay a strip of Duram Leak-Seal Tape (stick-stick, butyl mastic waterproofing membrane with a polyester backed reinforcing fabric) over the cured polyurethane sealant (as described above) pressing it firmly on the surface. Apply the Duram membrane directly over the tape and on the adjacent surfaces.

Joins, Gaps and Cracks

General: Joins, gaps and cracks should be suitably filled and sealed with an appropriate elastomeric sealant, preferably a polyurethane sealant, and allowed to cure.

Recommendation: The movement of small cracks should not be underestimated and should be at least covered with a flexible polyurethane sealant or additional coats of membrane.

Large or Live Cracks: Large cracks should be routed out to form a 'V' and then filled and sealed with a polyurethane waterproof joint sealant as per the manufacturer's instructions. The sealant should be finished slightly proud of the surface and allowed to cure.

After priming, as required, lay a strip of Duram Leak-Seal Tape over the join or crack pressing it firmly on to the substrate. The Duram membrane is then applied directly to the Duram Leak-Seal Tape and extending at least 75mm on to the adjacent surfaces.

If the Duram Leak-Seal is not used then a suitable bond breaker tape (such as duct tape) at least 48mm wide should be laid over the join or crack and apply a fully reinforced Duram membrane consisting of a base coat of membrane in to which the reinforcing fabric is embedded, a saturating coat of the Duram membrane ensuring that the fabric is entirely saturated and covered and then allowed to cure. At least one or two further coats are applied as per the Duram membrane's Product Data Sheet extending at least 75mm on to the adjacent surfaces.

Joins - Particularly in CFC Sheeting and Timber Sheeting

Ideally the sides of the sheets should be fully coated with a flexible polyurethane waterproof joint sealant prior to butting the sheets together.

If not, the joins should be suitably filled and sealed with an appropriate elastomeric polyurethane waterproof sealant and finished flush with or preferably slightly proud of the surface and allowed to cure.

After priming as required, lay a strip of Duram Leak-Seal Tape over the join, pressing it firmly on to the substrate. The Duram membrane is then as described under 'Large or Live Cracks'.

If the Duram Leak-Seal is not used then follow the procedure as described under 'Large or Live Cracks'.

Waste Outlets, Penetrations and Angles

Waste Outlets: Floor wastes and puddle flanges should be rebated in to the floor to allow water to readily drain. Gaps and perimeters should be sealed with a polyurethane sealant.

Plastic or metal angles: Where required by the Building Code such as internal hobs and exterior door barriers and also plastic corner angels under wall boards, they should be securely embedded in to a continuous, gap free bed of a polyurethane sealant / mastic.

Application

Stir well. Apply by brush, roller, soft broom or squeegee.

Apply in a minimum of two coats. To perform correctly the dry film thickness of the membrane must be at least 1.0mm to 1.2 mm.

Given that Azcothane Reo contains micro-fibres it is thereby internally reinforced and the use of an external reinforcing fabric is not required.

However, Azcothane Reo is suitable for use with a reinforcing fabric (Durascrium) and Leak Seal Tape.

Coverage

The stated average coverage rate may vary depending upon type, condition, porosity, texture of the surface and application technique.

Azcothane

Unreinforced: Minimum 1.5 litres to 1.8 litres per m², i.e 0.75 litres to 0.9 litres per m² per coat. A 15 litre pail will cover 10 m² for 2 coats at 1.0mm dry film thickness.

Reinforced: Minimum: 2.0 litres per m².

The dry film thickness for the unreinforced membrane must be at least 1.00mm and preferably 1.2mm.

Primers

Minimum 1 litre per 4m².

Colours

Azcothane Reo is available in white and grey. Special colours available upon request but minimum orders will apply.

Drying and Curing

Drying and curing of the product is affected by type, dryness and porosity of the surface, temperature, humidity, ventilation, climate conditions and application technique and therefore drying and curing can only be given as a guide.

Azcothane Reo is a fast drying water based product. Expected curing at 25°C at 50% RH: Touch dry: 4 to 6 hours per coat; Set: 12 hours; Full cure: 24 hours per coat. Ensure membrane is fully cured before tiling or topping.

Storage

Store in cool, dry area. Product is not flammable. Do not allow to freeze. Shelf life - about 12 months. Available in 4, and 15 Lt pails.

Clean Up

Wet spills can be cleaned with water, but spills should be avoided as it is difficult to remove entirely from porous surfaces.

Tiling, Topping or Top Coating

Azcothane Reo is compatible with most tile adhesives and 3:1 sand:cement beds.

Ideally the beds should be sealed / waterproofed to prevent the bed absorbing and holding water. Selection of the tile adhesive should be compatible with the flexibility of the substrate. Tiling must be done in accordance with AS3958.1-1991 and adequate expansion joints installed.

Safety & Precautions

Azcothane Reo is user friendly and safe to use if used correctly as intended. Nevertheless, protect eyes and skin and observe the safety precautions on the can and data sheet.

For full safety data refer to the products Material Safety Data Sheet. Observe precautions as per label.

Tests and Technical Data

Azcothane Reo's formulation complies with AS4858:2004 Wet Area Membranes as tested by the CSIRO.

Tensile Bond 2N/mm after 14 days

Application temperature range 10 to 35°C

Moisture Vapour Transmission 0.26 g/sq.m./24 hours

Elongation > 300% (Class 111 Extensibility)

CONDITIONS OF USE AND DISCLAIMER

The information contained in this data sheet is given in good faith based upon our knowledge and current information and does not imply warranty. The information is provided and the product sold on the basis that the product is used for its intended use and applied in a proper workman like manner in accordance with the instruction in this data sheet onto suitable and correctly prepared surfaces which shall remain sound, stable, free of structural defects, cracking, spalling concrete cancer, negative pressure, movement or other conditions that may effect the performance of the product. Deviations from application instructions may diminish or negate the performance of the product. Under no circumstances will the Company be liable for any loss, consequential or otherwise, arising from the use of the product. Liability is limited to the replacement of proven faulty product.